

REPORT DOCUMENTATION PAGE*Form Approved*
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY)		2. REPORT TYPE Conference Proceeding		3. DATES COVERED 06-11 July 2003	
4. TITLE AND SUBTITLE A Comparison of Biotic and Abiotic Sulphide Films on Alloy 400				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 601153N	
6. AUTHOR(S) Jason S. Lee, Richard I. Ray, Kristine Lowe and Brenda J. Little				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Naval Research Laboratory Oceanography Division Stennis Space Center, MS 39529-5004				8. PERFORMING ORGANIZATION REPORT NUMBER NRL/PP/7303/03/0053	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 800 N. Quincy St. Arlington, VA 22217-5660				10. SPONSOR/MONITOR'S ACRONYM(S) ONR	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT Distribution, tenacity and chemical composition of sulphide films produced by bacteria within biofilms were compared with those produced by waterborne inorganic sulphides. Attempts were made to differentiate corrosion mechanisms of alloy 400 (70Ni - 30Cu) exposed to seawater in the presence of absence of sulphate-reducing bacteria (SRB). Experiments were conducted in an anaerobic environment in the presence of inorganic sulphide and sulphate-reducing bacteria (SRB) either freely corrosion of coupled to an external cathode (alloy 400) exposed air. Sulphur concentration in the films increased in the presence of SRB as well as when samples were coupled to an external cathode. Bacteria encrusted with corrosion products and integrated into the sulphide film were only observed in the presence of SRB in addition to coupling with an external cathode.					
15. SUBJECT TERMS microbiologically influenced corrosion, nickel-copper alloys, sulphate reducing bacteria, sulphide attack					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
a. REPORT	b. ABSTRACT	c. THIS PAGE			Brenda Little
Unclassified	Unclassified	Unclassified	SAR	22	19b. TELEPHONE NUMBER (Include area code) 228-688-5494

20030826 064

PUBLICATION OR PRESENTATION RELEASE REQUEST

Pubkey: 3673

NRLINST 5600.2

1. REFERENCES AND ENCLOSURES	2. TYPE OF PUBLICATION OR PRESENTATION	3. ADMINISTRATIVE INFORMATION
Ref: (a) NRL Instruction 5600.2 (b) NRL Instruction 5510.40D	<input type="checkbox"/> Abstract only, published <input type="checkbox"/> Book <input type="checkbox"/> Conference Proceedings (refereed) <input type="checkbox"/> Invited speaker <input type="checkbox"/> Journal article (refereed) <input type="checkbox"/> Oral Presentation, published <input type="checkbox"/> Other, explain	<input type="checkbox"/> Abstract only, not published <input type="checkbox"/> Book chapter <input checked="" type="checkbox"/> Conference Proceedings (not refereed) <input type="checkbox"/> Multimedia report <input type="checkbox"/> Journal article (not refereed) <input type="checkbox"/> Oral Presentation, not published
Encl: (1) Two copies of subject paper (or abstract)		STRN <u>NRL/PP/7303-03-53</u> Route Sheet No. <u>7303/</u> Job Order No. <u>73-5052-13-5</u> Classification <u>X</u> <u>U</u> <u>C</u> Sponsor <u>ONR BASE</u> approval obtained <u>X</u> yes <u>no</u>

4. AUTHOR

Title of Paper or Presentation

A Comparison of Biotic and Abiotic Sulphide Films on Alloy 400

Author(s) Name(s) (First, MI, Last), Code, Affiliation if not NRL

Jason S. Lee, Richard I. Ray, Kristine Lowe, Brenda J. Little

It is intended to offer this paper to the Corrosion in the 21st Century

(Name of Conference)

06-JUL - 11-JUL-2003, Manchester, England, Unclassified

(Date, Place and Classification of Conference)

and/or for publication in Corrosion in the 21st Century, Unclassified

(Name and Classification of Publication)

(Name of Publisher)

After presentation or publication, pertinent publication/presentation data will be entered in the publications data base, in accordance with reference (a).

It is the opinion of the author that the subject paper (is) (is not X) classified, in accordance with reference (b).This paper does not violate any disclosure of trade secrets or suggestions of outside individuals or concerns which have been communicated to the Laboratory in confidence. This paper (does) (does not X) contain any militarily critical technology. This subject paper (has) (has never X) been incorporated in an official NRL Report.

Jason S. Lee, 7330

Name and Code (Principal Author)

(Signature)

5. ROUTING/APPROVAL

CODE	SIGNATURE	DATE	COMMENTS
Author(s) Lee		4/2	
Section Head N/A			
Branch Head Little		4/4/03	
Division Head Payne, acting		6/5/03	1. Release of this paper is approved. 2. To the best knowledge of this Division, the subject matter of this paper (has <u> </u>) (has never <u>X</u>) been classified.
Security, Code 7030.1		4/6/03	1. Paper or abstract was released. 2. A copy is filed in this office.
Office of Counsel, Code 1008.3		6/18/03	SSC-219-3
ADOR/Director NCST E.O. Hartwig, 7000			
Public Affairs (Unclassified/ Unlimited Only), Code 7030.4		6/17/03	
Division, Code			
Author, Code			

☒ **A - Approved for public release, distribution is unlimited.**

☐ **B - Distribution authorized to U.S. Government agencies only (check reason below):**

<input type="checkbox"/> Foreign Government Information	<input type="checkbox"/> Contractor Performance Evaluation	<input type="checkbox"/> Critical Technology
<input type="checkbox"/> Proprietary Information	<input type="checkbox"/> Administrative/Operational Use	<input type="checkbox"/> Premature Dissemination
<input type="checkbox"/> Test and Evaluation	<input type="checkbox"/> Software Documentation	<input type="checkbox"/> Cite "Specific Authority" _____ (Identification of valid documented authority)

Date statement applied _____

Other requests for this document shall be referred to _____
(Insert Controlling DOD Office*)

☐ **C - Distribution authorized to U.S. Government agencies and their contractors (check reason below):**

<input type="checkbox"/> Foreign Government Information	<input type="checkbox"/> Software Documentation	
<input type="checkbox"/> Administrative/Operational Use	<input type="checkbox"/> Critical Technology	<input type="checkbox"/> Cite "Specific Authority" _____ (Identification of valid documented authority)

Date statement applied _____

Other requests for this document shall be referred to _____
(Insert Controlling DOD Office*)

☐ **D - Distribution authorized to DOD and DOD contractors only (check reason below):**

<input type="checkbox"/> Foreign Government Information	<input type="checkbox"/> Critical Technology	
<input type="checkbox"/> Software Documentation	<input type="checkbox"/> Cite "Specific Authority" _____ (Identification of valid documented authority)	
<input type="checkbox"/> Administrative/Operational Use		

Date statement applied _____

Other requests for this document shall be referred to _____
(Insert Controlling DOD Office*)

☐ **E - Distribution authorized to DOD components only (check reason below):**

<input type="checkbox"/> Proprietary Information	<input type="checkbox"/> Premature Dissemination	<input type="checkbox"/> Critical Technology
<input type="checkbox"/> Foreign Government Information	<input type="checkbox"/> Software Documentation	<input type="checkbox"/> Direct Military Support
<input type="checkbox"/> Administrative/Operational Use	<input type="checkbox"/> Contractor Performance Evaluation	<input type="checkbox"/> Test and Evaluation

Date statement applied _____

Other requests for this document shall be referred to _____
(Insert Controlling DOD Office*)

☐ **F - Further dissemination only as directed by _____**
(Insert Controlling DOD Office*)

Date statement applied _____ or higher DOD authority _____

☐ **G - Distribution authorized to U.S. Government agencies and private individuals or enterprises eligible to obtain export-controlled technical data in accordance with regulations implementing 10 U.S.C. 140c.**

Date statement applied _____

Other requests for this document shall be referred to _____
(Insert Controlling DOD Office*)

*For NRL publications, this is usually the Commanding Officer, Naval Research Laboratory, Washington, DC 20375-5320

OTHER LIMITATION

<input type="checkbox"/> Classification	<input type="checkbox"/> NOFORN	<input type="checkbox"/> DTIC exempt (explain) _____
---	---------------------------------	--

Classification Review (Initial/Date) _____

Substantive changes made in this document after approval by Classification Review and Public Release invalidate these reviews. Therefore, if any substantive changes are made by the author, Technical Information, or anyone else, the document must be returned for another Classification Review and Publication Release.

INSTRUCTIONS

Author completes and submits this form with the manuscript via line channels to the division head for review and approval according to the routing in Section 4.

1. NRL Reports.....	Submit the diskette (if available), manuscript, typed double-spaced, complete with tables, illustrations, references, draft SF 298, and proposed distribution list.
2. NRL Memorandum Reports.....	Submit a copy of the original, typed manuscript complete with tables, illustrations, references, draft SF 298, and proposed distribution list.
3. NRL Publications or other books, brochures, pamphlets,.....	Handled on a per case basis by Site Technical Information Office.

proceedings, or any other printed publications.

A Comparison of Biotic and Abiotic Sulphide Films on Alloy 400

J.S. Lee, R.I. Ray, and B.J. Little

*Naval Research Laboratory, Code 7303 / 7330, Stennis Space Center,
MS 39529, jason.lee@nrlssc.navy.mil*

Abstract

Distribution, tenacity and chemical composition of sulphide films produced by bacteria within biofilms were compared with those produced by waterborne inorganic sulphides. Attempts were made to differentiate corrosion mechanisms of alloy 400 (70Ni-30Cu) exposed to seawater in the presence or absence of sulphate-reducing bacteria (SRB). Experiments were conducted in an anaerobic environment in the presence of inorganic sulphide and sulphate-reducing bacteria (SRB) either freely corroding or coupled to an external cathode (alloy 400) exposed to air. Sulphur concentration in the films increased in the presence of SRB as well as when samples were coupled to an external cathode. Bacteria encrusted with corrosion products and integrated into the sulphide film were only observed in the presence of SRB in addition to coupling with an external cathode.

Keywords: microbiologically influenced corrosion, nickel-copper alloys, sulphate reducing bacteria, sulphide attack

Introduction

Determination of specific mechanisms for corrosion due to microbiologically mediated oxidation and reduction of sulphur is complicated by (1) the variety of potential metabolic/energy sources and by-products, (2) the coexistence of reduced and oxidized sulphur species, (3) competing reactions with inorganic and organic compounds, and (4) the versatility and adaptability of microorganisms

in biofilms. The physical scale over which the sulphur cycle influences corrosion varies with environment. As illustrated in Figure 1, the complete sulphur cycle of oxidation and reduction reactions can take place in macro (bulk) environments, including sewers and polluted harbours or within the microenvironment of biofilms.




Figure 1. Possible reactions within a biofilm. Sulphur cycle highlighted.

Most of the literature on sulphide induced corrosion of copper and nickel alloys does not differentiate between corrosion due to waterborne sulphides and sulphides produced by sulphate-reducing bacteria (SRB) within biofilms. The problem of accelerated corrosion of copper/nickel and nickel/copper alloys by waterborne sulphides was identified in the 1970's and early 1980's [1-3]. In most cases, investigators used laboratory experiments in which 90/10 or 70/30 copper/nickel alloys were exposed to artificial or natural seawater with sodium sulphide. Gudas and Hack [4] demonstrated that inorganic sulphide films enhanced galvanic corrosion under some circumstances. In the 1980's, Syrett [5-7] demonstrated that deaerated seawater containing dissolved inorganic sulphides did not immediately lead to accelerated corrosion. Instead, a porous sulphide corrosion product interfered with the formation of an oxide film on

subsequent exposures to oxygenated seawater. In the mid 1980's investigators recognized that most failures of copper and nickel alloys in actual seawater service were related to *in situ* sulphide production by SRB in biofilms.

Nickel/copper alloy 400 (Monel 400), nominally containing 66.5% nickel, 31.5% copper and 1.25% iron, is used for seawater and brackish water handling because of its resistance to chloride-ion stress corrosion cracking and erosion corrosion. However, alloy 400 is prone to pitting in chloride-containing environments where the passive film can be disturbed. Under stagnant conditions chlorides penetrate the passive film at weak points and cause pitting attack. Sulphides can cause either a modification of the oxide layer as described for copper or breakdown of the oxide film of nickel alloys. Pit initiation and propagation depend on depth of exposure, temperature and presence of surface deposits. Friend [8] established that nickel/copper alloys containing more than 30% nickel formed a passive film similar in structure to that formed on pure nickel. Localized corrosion of alloy 400 in seawater service is related to stagnation and/or intermittent flow [9, 10].

Experimental

Materials

Disk shaped alloy 400 coupons (1.58 cm diameter x 0.158 cm thick) were purchased with an as-mill finish (Metal Samples, Munford, Alabama, USA). Chemical composition provided with the samples can be seen in Table 1. 100 cm long wire leads were electrically attached to the back of the samples by carbon tape and silver adhesive. Connections were strengthened by applying a bead of hot-glue. Samples were embedded in EpoThin epoxy (Buehler Ltd, Lake Bluff, IL, USA) with the bare surface facing down. The epoxy created a watertight seal at the connections. Samples were wet-polished to a 1200 grit finish, sonicated in acetone for 5 minutes, rinsed with ethanol, and blown dry with nitrogen gas.

Table 1. Chemical composition of alloy 400 in wt%.

Ni	Cu	Mn	Si	Fe	S	P	Al	Pb	C	Zn
63.76	31.95	1.11	0.14	2.25	0.003	0.002	0.03	0.002	0.132	0.010

Description of microbial cultures

SRB used in the current study have been described previously [10–12]. They include:

P10 – isolated from a 4140 steel coupon with a 5 step iron phosphate primer (no topcoat) in a constant immersion flume tank (marine water) at the Naval Surface Warfare Center (NSWC)/Ft. Lauderdale, FL.

P14 – isolated from a 4140 steel coupon with a 5 step iron phosphate primer + an epoxy topcoat in a constant immersion flume tank (marine water) at NSWC/Ft. Lauderdale, FL.

49Z – isolated from a 4140 steel coupon with a zinc primer (no topcoat) in a constant immersion flume tank (marine water) at NSWC/Ft. Lauderdale, FL.

CG59 – isolated from the seawater piping system of a surface ship at Long Beach Naval Station, Long Beach, CA (marine water).

C130 – isolated from aluminium alloy with an epoxy primer + polyurethane topcoat from moisture trapped under the cargo ramp of a C-130 transport plane at the Naval Air Depot (Cherry Point, NC).

All isolates are positive for desulfovirdin (characteristic of *Desulfovibrio sp.*). 100-ml stock cultures of SRB were maintained in liquid growth medium (Postgate's B) [13] supplemented with NaCl (3% w/v). Cultures were kept in glass bottles fitted with rubber septa and aluminium crimped tops and were placed in glass canisters with an anaerobic gas generating system (BBL™ Gas Pak Plus™; Becton Dickinson Co., Sparks, MD) at 30°C until use.

Sulphide Concentration Measurements

Dissolved sulphide (S^{2-}) was determined by the methylene blue method [14]. Briefly, 0.5 ml of an amine-sulphuric acid solution and 0.15 ml of concentrated $FeCl_3$ solution was added to 7.5 ml of fresh sample in a clean cuvette. The mixture was capped and inverted one time. After 3 minutes, 1.6 ml of 50% $(NH_4)_2HPO_4$ was added and the mixture inverted one time. After 5 minutes, the cuvette was placed in a Hach Model DR/2500 spectrophotometer (Hach Co., Loveland, CO) and S^{2-} concentrations were determined by a factory-installed program (# 690) for sulphide determination.

Reactor Set-up

Three 1.5 litre glass jars were filled with 1350 ml of artificial seawater (ASW) (35 ppt salinity, pH = 8.2). 150 ml of Postgate's B media was also added to make a suitable environment for bacterial growth. Jars were labelled '+SRB', 'uninoculated', and 'aerobic'. In each of the first two jars, two mounted alloy 400 samples were placed with the exposed sample face in the vertical orientation. Three samples were similarly placed in the aerobic jar. Nitrogen gas was bubbled through the first two jars for 15 minutes to purge oxygen. The first two jars were then placed in an anaerobic hood which contained an atmosphere of 5% carbon dioxide, 10% hydrogen, and the balance nitrogen (Figure 2). A single saturated calomel reference electrode (SCE) was placed inside the anaerobic chamber in a beaker of saturated KCl solution. KCl salt bridges extending from each jar were placed into this beaker for continuous solution conductivity between the jars. Each electrode was connected to a data logger which measured the corrosion potential vs. SCE every 10 minutes. No attempt was made to insure sterile conditions throughout the experiment. The anaerobic chamber was maintained at 30 °C which has been shown to be the optimum temperature for SRB growth [9, 15].




Figure 2. Schematic of the experimental set-up. Anaerobic chamber contained 5% carbon dioxide, 10% hydrogen, and the balance nitrogen. A septum on the outside wall of the anaerobic chamber provided access for wire connections and salt bridges between jars.

Experimental Run

3 ml of each of the five SRB cultures were added to the +SRB jar. Initial dissolved sulphide concentration in the bulk solution was measured to be 3.67 ppm. An attempt was made to keep the initial dissolved sulphide concentration of the two jars by adding 4 ppm Na_2S to the uninoculated jar for a final concentration of 3.72 ppm sulphide. One sample from each jar in the anaerobic hood was electrically coupled (by wire) to a corresponding sample in the 'aerobic' jar. After 40 hrs, bulk dissolved sulphide concentrations of the bulk solution were measured: 4.17 ppm for +SRB, 0.57 ppm for uninoculated. 4 ppm Na_2S was added to uninoculated jar for a final bulk concentration of 3.67 ppm sulphide. Sulphide concentrations were taken again at $t = 68, 140, \text{ and } 184$ hrs (concentrations are listed in Figure 3). After 70 hrs the coupled anaerobic samples were disconnected from their corresponding aerobic samples and left to freely corrode. At $t = 184$

hrs, all samples were removed, rinsed through a series of ASW and distilled water dilutions to remove salts. Sample surfaces were examined using an environmental scanning electron microscope (ESEM), and corrosion products were characterized by energy dispersive spectroscopy (EDS).

Results

Figure 3 indicates the dependence of potential vs. time over the 184 hr experimental duration. The non-coupled sample in the aerobic jar (black curve) started at ~ -550 mV and rose to ~ -300 mV over the first 18 hours. For the duration of the experiment, potential values (black curve) ranged from -275 to -425 mV. The freely corroding (not coupled) +SRB sample (blue curve) started at -600 mV, dropped to -650 mV in the first day and remained between -650 and -700 mV for the duration of the experiment. The freely corroding uninoculated sample (orange curve) started at -640 mV, rose to -570 mV over the first day, dropped to -650 mV when sulphide was added at $t = 40$ hrs, and remained stable until the end of the experiment. Both coupled samples, +SRB (green curve) and uninoculated (pink curve) initially followed the potential rise of the aerobic sample (black curve) to -400 mV over the first 18 hours. At $t = 18$ hours the curves began to diverge, with the aerobic sample rising to -300 mV, the +SRB curve sample dropping to -650 mV and the uninoculated sample dropping to -500 mV. At 40 hrs, the bulk dissolved sulphide concentration in the uninoculated case was raised to 3.67 ppm and potential dropped to -600 mV. Over the next 30 hrs, potential rose to -550 mV. At $t = 68$ hrs, bulk sulphide concentrations of the +SRB and uninoculated cases were 4.17 and 2.58 ppm respectively. Also at 70 hrs, the couples were disconnected and both anaerobic samples potential immediately decreased by 50 mV. Over the next day, the uninoculated sample continued to drop to -650 mV at which time it followed the freely corroding uninoculated sample (orange curve) out to the end of the experiment, ending with potential of -640 mV. The +SRB sample also follows this trend but matches +SRB sample which was freely corroding with a final potential = ~ -660 mV. Final dissolved sulphide concentration in ppm was 1.54 (+SRB) and 1.06 (uninoculated).




Figure 3. Potential dependence and sulphide concentrations over the course of 184 hrs. Light blue line indicates when the couples were disconnected at 40hrs. Sulphide concentrations (ppm) taken at $t = 0, 40, 68, 140$ and 184 are black numbers with +SRB case on top and uninoculated case below.

At the conclusion of the experiment, each sample was examined visually. +SRB samples had very dark and uniform surface deposits which were very adherent, with the coupled sample being the darkest. The uninoculated samples had patching dark surface deposits which easily flaked off during removal of salts. As mentioned previously, sterile conditions were not maintained in any way. This can be seen in Figure 4, which includes ESEM micrographs of the freely corroding samples in both +SRB and uninoculated conditions. Cells can be readily seen in each picture as cylindrical dark spots indicating microorganisms not associated with any corrosion products. The blue arrow in the +SRB picture indicates an individual SRB identified by its comma shape. Microorganisms can be seen in the uninoculated case as well, but no attempt was made to determine the types. At low magnification, both cases looked very similar with numerous bacteria and the polishing lines still visible. At higher magnification

differences arose. In the +SRB case, the micrographs indicate that the surface is completely vitrified and contained high contrast slivers (seen as white lines). EDS indicated that the white slivers were of the same composition as the surrounding darker deposit. In the uninoculated case, the surface was covered with small, distributed deposits spread over the surface. EDS determined the +SRB surface deposit to be composed of 8% sulphur, while the uninoculated distributed deposits consisted of 2% sulphur. It should be noted that none of the microorganisms were coated by corrosion products.




Figure 4. ESEM micrographs and corresponding EDS of surface deposits after 184 hrs exposure to +SRB and uninoculated conditions with freely corroding samples (not coupled) at two magnifications. Distribution, structure, and composition of sulphides can be seen to be different for the two cases. Important to notice that the sulphide concentration in the "+SRB" was 4x larger than the uninoculated case. Blue arrow indicates individual SRB. No encrusted cells seen.

Figure 5 includes ESEM micrographs of the initially coupled samples in both +SRB and uninoculated conditions. At low magnification, cells are seen as dark spots in each case indicating microorganisms not associated with any corrosion products. In the +SRB case, large cracks can be seen running through the surface deposit. In the uninoculated case, a large deposit covering the left of the image can be seen with corrosion products appearing from under the deposit. At higher magnification in the +SRB case, the surface deposit appeared vitrified with encrusted cells embedded in the deposit (blue arrow). In the uninoculated case, the surface was covered with small, distributed deposits spread over the surface with a large deposit covering the bottom part of the image. EDS determined the +SRB surface deposit to be composed of 16% sulphur, while the uninoculated distributed deposits consisted of 9% sulphur. Notice the microorganisms in the uninoculated case are associated with the corrosion products but are not encrusted.




Figure 5. ESEM micrographs and corresponding EDS of surface deposits after 184 hrs exposure to +SRB and uninoculated conditions initially coupled for the first 70 hrs at two magnifications. Distribution, structure, and composition of sulphides can be seen to be different for the two cases. Sulphide concentration in the "+SRB" has increased to 16%. Blue arrow indicates individual SRB encrusted with corrosion products.

Discussion

It is well established that alloy 400 is susceptible to SRB influenced corrosion [9, 15, 16]. The process is as follows: as a result of microbial respiration, SRB within a biofilm reduce the sulphate in seawater (2 gm L^{-1}) to sulphide. The sulphides react with the copper/nickel oxides to produce a sulphur-rich layer. Sulphide layers on alloy 400 form rapidly, causing acceleration in the corrosion rate during its formation. Maxwell [17] and later Hamilton and Maxwell [18] demonstrated the presence of SRB in anaerobic niches of biofilm exposed to aerobic seawater. They surmised that upon exposure to oxygenated flowing seawater the sulphide layer would peel away in patches leaving bare metal exposed, thus creating an oxygen concentration cell which would provide new metal for corrosion attack. In this model, the aerated seawater supplies oxygen as a cathodic reactant to push the corrosion rate higher. However, this is often difficult to reproduce in the laboratory because of the unpredictability of sloughing, and the subsequent destruction of the biofilm's integrity. It was with this idea that the current authors designed this experiment in which cathodic current would be supplied remotely to a sample of alloy 400 exposed to dissolved sulphides produced by SRB. This experiment was designed to simulate the affect of oxygen on the corrosion behaviour without removing the biofilm. Removal of the couple after 40 hrs (thus removing the remote cathodic current) was meant to simulate the decrease in oxygen as a closed environment transforms from aerobic to anaerobic conditions.

Gouda *et al.* [16] studied the electrochemical behaviour of copper-containing alloys in seawater exposed to sulphides and SRB. Using polarization resistance (R_p) and anodic polarization scans, they demonstrated that passivation of the metal surface occurred upon initial exposure of alloy 400 to an SRB environment. As seen in Figure 3, ennoblement of the coupled samples followed the rising potential of the aerobic sample over the first 18 hrs. While these data may indicate passivation of the alloy 400 surface, they more likely indicate the coupled samples were cathodically controlled over this time (by the aerobic electrode), corresponding with the build-up of dark surface deposits seen on both "+SRB" and "inoculated" surfaces in the first 18

hours. This process seems to be independent of whether SRB are present or not. However, at 18 hrs, differences are observed. The +SRB potential drops from -440 mV down to -650 mV while the uninoculated potential drops from -410 mV only down to -500 mV. The difference in magnitude for the potential drops between +SRB and uninoculated cases is possibly due to the formation of a patching SRB biofilm in the +SRB case which allowed the sulphide concentration at the metal/biofilm interface to increase, thereby, decreasing the potential. In contrast, the uninoculated case which did not contain intentionally inoculated SRB, would not decrease in potential as much due to the lower sulphide concentration. Bulk sulphide concentration increasing over the first 40 hrs in the +SRB case indicated the presence of growing SRB and the presence of a dark surface film indicates the incorporation of sulphide into the alloy 400 surface oxide. However, dissolved sulphide concentration in the uninoculated case declined steeply over the first 40 hrs indicating sulphide was not being produced. It should be noticed that throughout the experiment, the potential of the coupled +SRB case was always lower than the coupled 'inoculated' case. This trend was also observed in the freely corroding samples.

Differences in sulphides produced by bacteria within biofilms and waterborne inorganic sulphides were identified. Sulphide layers formed in biofilms during exposure to ASW + SRB covered the entire surface of the sample. In contrast, exposure to uninoculated ASW and inorganic sulphides resulted in only localized sulphide deposits covering a fraction of the metal surface. Sulphide layers formed in biofilms were also more tenacious towards removal during rinsing with distilled water than those formed in the uninoculated case. The tenacity of the SRB sulphide layers may be due to the extra cellular polymeric substances (EPS) produced within the SRB biofilm. EPS may act as an adhesive that thereby strengthens the sulphide layer against sloughing. Lee *et al.* [19] found similar results in the corrosion of alloy 400 in the presence of SRB.

Chemical composition of sulphide layers produced by exposure to uninoculated and SRB containing seawater also differed. Figure 6 demonstrates the difference found in sulphur concentration between

the different cases. In the case of freely corroding samples, the +SRB corrosion products had a high sulphur concentration of 8%, while uninoculated products were composed of only 3% sulphur. In the case of the coupled samples, the sulphur concentration increased to 16 and 9% for the +SRB and uninoculated cases, respectively. The higher concentration of sulphur in the SRB containing media as probably due to the production of sulphides at the biofilm/metal interface. The higher concentration of sulphur due to coupling can be attributed to a combined affect of increased reactivity at the metal surface due to a driving cathodic current, increased activity of metal ions bound to SRB (see below) and the attraction of bacteria to the anodic electrode by electrostatic forces [20]. Sulphur concentration in the +SRB layer is especially high considering the bulk solution had a sulphide concentration of ~4 ppm. These findings indicate a connection between bacterial activities and the resulting surface morphology found in this system. Active bacterial surface-mediated mineralisation occurs either by the direct transformation of metals (i.e., methylation, redox reactions) or by the formation of metal-reactive by-products (i.e., sulphate reduction producing sulphide). Experimental work with cultures of SRB has shown that metal ions sorbed to bacterial cells tend to be more chemically active than when they are in solution [21] and reduced iron and other base metals are commonly precipitated on dissimulatory SRB cell surfaces as sulphides [22].




Figure 6. Comparison of sulphur concentration in the corrosion layers as a function of coupling and the presence of SRB.

Another observation related to the SRB on the surface of alloy 400 was that cells were encrusted in copper/nickel sulphides only when the sample was initially coupled to the external cathode and SRB were present. Bacteria require Cu and Ni as trace inorganic nutrients but excessive quantities are inhibitory or lethal. Microorganisms immobilize, mobilize or transform metals by extra cellular precipitation reactions, intracellular accumulation, oxidation and reduction reactions, methylation and demethylation, and extra cellular binding[23]. These mechanisms impede toxic metals from entering and killing the cell. Bacteria can react with soluble metals by binding and precipitating metal ions on their surface, producing minerals. Precipitation reactions can be divided into two general categories: passive and active mineralization [22]. Passive mineralisation, or surface catalysis, is caused by the net negative charge on most bacterial cell surfaces which nucleates the precipitation of metallic cations from solution. In many bacteria, capsules or slime, consisting of extra cellular polymers, represent the outermost layer of the cell surface. Capsules consist of linear polymers of polysaccharides or repeating amino acid units and contain over 90% water. They may contain anionic moieties such as carboxyl groups, and occasionally phosphate and sulphate groups, which enable them to bind metals

[24, 25]. Bacterial extra cellular polymers have been proposed as carriers for metals in aquatic environments [26]. Binding sites for metals are also found in proteins, nucleic acids and specialized [27]. Complexing ligands may be necessary for binding of specific metals; in aqueous solutions, metals ions are often hydrated and can be attracted to a number of dissolved, colloidal or solid organic or inorganic substances [24]. Metal binding to cell surfaces is pH and temperature dependent due to their influence on metal and cell wall chemistry [28–30]. Passive metal binding by bacterial surfaces represents an electrostatic interaction; consequently, it is not necessary that the cells be viable, only that their surfaces remain intact [24].

Gouda *et al.* [9, 15] examined the susceptibility of alloy 400 towards microbial attack in Arabian Gulf seawater. Results indicated that SRB attack is initiated beneath black sulphur-rich deposits. The deposits were found to be mostly iron nickel sulphides. No corrosion was detected after 3 weeks of exposure under anaerobic SRB conditions, but upon addition of aerated solution, the corrosion rate increased significantly. The authors stated that failure of alloy 400 heat exchanger tubes could take place if SRB are present irrespective of their concentration. Also, their results indicated that alloy 400 is highly susceptible to SRB attack when compared to 70/30 Cu–Ni alloy, brass or N08825 under the same conditions. The mode of SRB attack was intergranular corrosion that was accompanied by selective dealloying of nickel and iron. Using EDS they found that under black iron and nickel sulphides severe intergranular corrosion had taken place. The attacked regions were copper-rich while the regions around the active sites had higher Ni concentrations. Black deposits were also found to be devoid of appreciable copper compounds which indicated preferential attack of nickel and iron. However, a green corrosion layer, found on top of these black deposits, was composed of mainly copper chloride indicating that copper corrosion took place after the initial sulphide attack.

Further experiments are needed to better understand the mechanisms behind this type of corrosion such as characterization of the different minerals produced during corrosion using an x-ray diffraction

spectrometer. EDS provides chemical composition but not phase identification. Also, a Fourier Transform infrared microscope could be used to identify organic compounds which are produced only in the presence of an SRB biofilm. Finally, removal of the corrosion products to characterize the resulting corrosion morphology in each case is a necessity.

Conclusions

Distribution, tenacity and chemical composition of sulphides produced by SRB within biofilms are different from those produced by waterborne inorganic sulphides. In an anaerobic environment, SRB within biofilms produce sulphides at the metal surface which lead to an increase in sulphur content of the corrosion products. Coupling to an external cathode exposed to aerobic conditions increase the sulphur content further. Because bacteria enmeshed in biofilms produce extra cellular polymeric materials the tenacity of sulphide layers produced by SRB may differ from those produced in the absence of SRB. In the experiments described, only the sample exposed to SRB and coupled to an external cathode had encrusted bacteria embedded within the sulphide layer.

Acknowledgements

The authors wish to thank J. Jones-Meehan for supplying the bacterial samples and K. I. Lowe for the maintaining of the bacterial cultures.

The work was performed under program element 0601153N, contribution number NRL/pp/7303/03/0053.

References

1. "The influence of corrosion product structure on the corrosion rate of Cu-Ni alloys", J. F. North and M. J. Pryor, *Corrosion Science*, 10, pp.297-311, 1970.
2. "Potential-pH diagrams for 90-10 and 70-30 Cu-Ni in sea water", K. D. Efrid, *Corrosion*, 31, 3, pp.77-83, 1975.

3. "The influence of biofouling countermeasures on corrosion of heat exchanger materials in sea water", R. O. Lewis, *Materials Performance*, 21, 9, pp.31-38, 1982.
4. "Sulfide induced corrosion of copper-nickel alloys", J. P. Gudas and H. P. Hack, *Corrosion*, 35, 2, pp.67-73, 1979.
5. "The mechanism of accelerated corrosion of copper-nickel alloys in sulphide-polluted seawater", B. C. Syrett, *Corrosion Science*, 21, 3, pp.187-209, 1981.
6. "Corrosion of copper-nickel alloys in seawater polluted with sulphide and sulphide oxidation products", B. C. Syrett, D. D. MacDonald and S. S. Wing, *Corrosion*, 35, 9, pp.409-422, 1979.
7. "Accelerated corrosion of copper in flowing pure water contaminated with oxygen and sulfide", B. C. Syrett, *Corrosion*, 33, 7, pp.257-262, 1977.
8. "Corrosion of Nickel and Nickel-Based Alloys", W. Z. Friend, ed., Houston, TX: NACE International International, 1980.
9. "Microbial-induced corrosion of Monel 400 in seawater," V. K. Gouda, I. M. Banat, W. T. Riad and S. Mansour, Paper no. 107, CORROSION / 90, NACE International, 1990.
10. "Microbiologically influenced corrosion in copper and nickel seawater piping systems", B. J. Little, P. A. Wagner, R. I. Ray and M. B. McNeil, *Marine Technology Society Journal*, 24, 3, pp.10-17, 1991.
11. "Corrosion resistance of several conductive caulks and sealants from marine field tests and laboratory studies with marine, mixed communities containing sulfate-reducing bacteria (SRB)," J. Jones-Meehan, K. L. Vasanth, R. K. Conrad, M. Fernandez, B. J. Little and R. I. Ray, In Microbiologically Influenced Corrosion Testing, ASTM STP 1232, Philadelphia, PA: American Society for Testing and Materials, 1994.

12. "Microbiologically influenced corrosion of epoxy- and nylon-coated steel by mixed microbial communities," M. Walch and J. Jones-Meehan, Paper no. 112, CORROSION / 90, NACE International, 1990.
13. "The Sulfate Reducing Bacteria", J. R. Postgate, ed., New York, NY: Cambridge University Press, 1984.
14. "Method 4550D," L. S. Clesceri, A. E. Greenberg and A. D. Easton, In Standard Methods for the Examination of Water and Wastewater, Washington, DC: American Public Health Association, 1998.
15. "Microbiologically induced corrosion of UNS alloy 400 in seawater", V. K. Gouda, I. M. Banat, W. T. Riad and S. Mansour, *Corrosion*, **49**, 1, pp.63-73, 1993.
16. "The effect of sulphate-reducing bacteria on the electrochemical behavior of corrosion-resistant alloys in sea water", V. K. Gouda, H. M. Shalaby and I. M. Banat, *Corrosion Science*, **35**, 1-4, pp.683-691, 1993.
17. "Biological and corrosion activities of sulphate-reducing bacteria within natural biofilms", S. Maxwell, Ph.D. Dissertation, Department of Microbiology, University of Aberdeen, 1983.
18. "Biological and corrosion activities of sulphate reducing bacteria within natural biofilms," W. A. Hamilton and S. Maxwell, In Biologically Induced Corrosion, Houston, TX: NACE International, 1985.
19. "Corrosion mechanisms of UNS alloy 400 in sea water," J. S. Lee, K. I. Lowe, R. I. Ray and B. J. Little, Paper no. 03214, CORROSION / 2003, NACE International International, 2003.
20. "The role of bacteria in pit propagation of carbon steel", M. J. Franklin, D. C. White, B. J. Little, R. I. Ray and R. K. Pope, *Biofouling*, **15**, 1-3, pp.13-23, 2000.

21. "The role of sulfate-reducing bacteria in the deposition of sedimentary uranium ore", A. Mohagheghi, D. F. Updegraff and M. B. Goldhaber, *Geomicrobiology Journal*, 4, pp.153-173, 1985.
22. "Bacterial surface-mediated mineral formation," G. Southam, In *Environmental Microbe-Metal Interactions*, Washington, DC: ASM Press, 2000.
23. "Bioremediation of metal contaminated surface and groundwaters", C. L. Brierley, *Geomicrobiology Journal*, 8, 3-4, pp.201-223, 1990.
24. "Metal-binding capacity of bacterial surfaces and their ability to form mineralized aggregates," R. J. C. McLean and T. J. Beveridge, In *Microbial Mineral Recovery*, New York, NY: McGraw-Hill, Inc., 1990.
25. "Precipitation of metallic cations by the acidic exopolysaccharides from *Bradyrhizobium japonicum* and *Bradyrhizobium chamecypitissus* strain BGA-1", J. Corzo, M. Leonbarrios, V. Hernandorico and A. M. Gutierreznavarro, *Applied and Environmental Microbiology*, 60, 12, pp.4531-4536, 1994.
26. "Mobilization of absorbed cadmium and lead in aquifer material by bacterial extracellular polymers", J. H. Chen, L. W. Lion, W. C. Ghiorse and M. L. Shuler, *Water Research*, 29, 2, pp.421-430, 1995.
27. "The function of metals in microorganisms," M. N. Hughes and R. K. Poole, In *Metals and Microorganisms*, New York, NY: Champman and Hall, 1989.
28. "Uptake of metals by bacterial polysaccharides", J. L. Geddie and I. W. Sutherland, *Journal of Applied Bacteriology*, 74, 4, pp.467-472, 1993.

29. "Uranium biosorption by a filamentous fungus, *Mucor miehei*. pH effect on mechanisms and performances of uptake", E. Guibal, C. Roulph and P. Lecloire, *Water Research*, 26, 8, pp.1139-1145, 1992.

30. "Heavy metals alter the electrokinetic properties of bacteria, yeasts and clay minerals", Y. E. Collins and G. Stotzky, *Applied and Environmental Microbiology*, 58, 5, pp.1592-1600, 1992.